

410-R-759 QC/QA HMA - SMA PAVEMENT

(Revised 10-19-23)

The Standard Specifications are revised as follows:

SECTION 410, BEGIN LINE 24, DELETE AND INSERT AS FOLLOWS:

Asphalt Materials

- PG Binder, PG ~~76-22~~, PG ~~70-22~~, ~~58E-28~~902.01(a)
- Coarse Aggregates, Class AS.....904.03
- Fine Aggregates (sand, mineral filler).....904.02
- Stabilizing Additives *AASHTO M 325

**The stabilizer shall be virgin cellulose or virgin mineral fiber.*

410.04 Design Mix Formula

A DMF shall be prepared in accordance with 410.05 and submitted in a format acceptable to the Engineer one week prior to use. The DMF shall state the maximum particle size in the mixture. The DMF shall state the calibration factor, test temperature and absorption factors to be used for the determination of binder content using the ignition oven in accordance with ITM 586, the binder content by extraction in accordance with ITM 571, ΔPb, determined in accordance with ITM 591, the aggregate degradation loss value in accordance with ITM 220 and a Mixture Adjustment Factor, MAF. The DMF shall state the source, type dosage rate of any stabilizing additives. The DMF ~~will~~ shall be based on the ESAL and mixture designation. No mixture shall be used until the DMF has been assigned a mixture number by the DTE.

The ESAL category ~~identified in the pay item correlates to the following ESAL ranges:~~ shall be ESAL Category 4 corresponding to greater than or equal to 10,000,000 ESALs.

ESAL Category	ESAL
2*	< 3,000,000
3	3,000,000 to < 10,000,000
4*	≥ 10,000,000
* A category 2 mixture shall replace a category 1 mixture and a category 4 mixture shall replace a category 5 mixture.	

The plant discharge temperature for any mixture shall not be more than ~~315°F whenever PG 70-22 binder is used or not more than 325°F whenever PG 76-22 binder is used~~. SMA may be produced using a water-injection foaming device. The DMF shall list the minimum and maximum plant discharge temperatures as applicable to the mixture.

SECTION 410, BEGIN LINE 99, DELETE AS FOLLOWS:

A PG binder ~~grade or~~ source change will not require a new mix design. ~~If the upper temperature classification of the PG binder is lower than the original PG grade, a new TSR value is required.~~

SECTION 410, BEGIN LINE 110, INSERT AS FOLLOWS:

410.06 Recycled Materials

Recycled materials shall be in accordance with 401.06 for dense graded mixtures except *RAS shall not be used and* non-SMA RAP material for use in the SMA mixture shall be 100% passing the 3/8 in. (9.5 mm) sieve and 95 to 100% passing the No. 4 (4.75 mm) sieve.

SECTION 410, BEGIN LINE 260, DELETE AS FOLLOWS:

mechanical devices may be placed by other methods. The temperature of mixture at the time of spreading shall be no more than ~~315°F whenever PG 70-22 binder is used or no more than 325°F whenever PG 76-22 binder is used~~. The temperature of each mixture shall not be less than 245°F at the time of spreading when placed with paving equipment in accordance with 409.03(c)2 or 409.03(c)3. No mixture shall be placed on a previously paved course that has not cooled to less than 175°F.

SECTION 410, BEGIN LINE 525, DELETE AND INSERT AS FOLLOWS:

Payment will be made under:

Pay Item	Pay Unit Symbol
Joint Adhesive, _____ course type	LFT
QC/QA - HMA, <u>4</u> , <u>58E</u> , _____ mm, - SMA (ESAL ⁽¹⁾)(PG ⁽²⁾)(Course ⁽³⁾)(Mix ⁽⁴⁾)	TON
Quality Assurance Adjustment	DOL

⁽¹⁾ ESAL Category as defined in 410.04

⁽²⁾ Number represents the high temperature binder grade. *Letter represents traffic loading designation*. Low temperature grades is - ~~2228~~

⁽³⁾ Surface or Intermediate

⁽⁴⁾ Mixture Designation